
EDGING PLEAT HARD ANODISED ALUMINIUM



ΤΥΡΕ	Edging	
RANGE	Designer Stair Edging	
DESIGN	Pleat	
MATERIAL	6063 T5 extruded aluminium alloy	
FINISH	Hard anodised	



FEATURES

Extruded intermittent smooth plates encased between a continuous corduroy pattern designed by DTAC in Australia

Available in exclusive premium quality flat, angle or carpet profiles

Suitable for all stable finished indoor or outdoor surfaces and substrates

PAGE 1 OF 3

DTAC

Designed to comply with AS 1428.1 Design for Access and Mobility Part 1: General Requirements for Access — New Building Work

Tested for compliance with slip resistance requirements as detailed in HB 198

Backed by 2 year warranty

NCC COMPLIANT

National Construction Code (NCC) compliant products are designed to comply with the NCC—and Disability (Access to Premises—Buildings) Standards to meet the deemed-to-satisfy-provisions

SLIP RESISTANCE TESTING

Important information: To determine a classification of a slip resistance rating, see Australian Standards Hand Book 198 (HB 198), an Introductory Guide to Slip Resistance of Pedestrian Materials. This document outlines the minimum ratings of a location and situation of a pedestrian surface.

TEST	Wet Pendulum Test — AS 4586 APPENDIX A		
FOUR S 96 SLIDER	= 64 CLASS = P5		
TRL 55 SLIDER	= 50 CLASS = P4		
TEST	Dry Floor Friction Test — AS 4586 APPENDIX B		
MEAN COF	= 0.50 CLASS = D1		
TEST	Wet/Barefoot Ramp Test — AS 4586 APPENDIX C		
MEAN ANGLE OF INCL	LINATION = 28° CLASS = C		
TEST	Oil/Wet Ramp Test — AS 4586 APPENDIX D		
CORRECTED MEAN OVERALL ACCEPTANCE ANGLE = 27.2° CLASS = R12			

LUMINANCE TESTING

Important information: To determine a luminance contrast between a substrate and the DTAC EDGING, see: AS 1428.1:2009. DTAC can test your substrate for luminance contrast to give you peace of mind that your DTAC project will be fully compliant to AS 1428.1.

TEST	Design for Access & Mobility — AS 1428.1 APPENDIX B		
NATURAL			
LUMINANCE	E REFLECTANCE RATING / WET	= 57.8	
LUMINANCE REFLECTANCE RATING / DRY		= 58.2	
BLACK			
LUMINANCE	E REFLECTANCE RATING / WET	= 4.4	
LUMINANCE	E REFLECTANCE RATING / DRY	= 5.4	

DTAC PTY LTD ABN 41 093 070 127

Unit 4, 11-12 Phillip Court Port Melbourne Victoria Australia 3207


PO Box 5059 South Melbourne Victoria Australia 3205 PEMKO®

T 1300 793 478 F 1300 780 628

estimating@dtac.com.au www.dtac.com.au

© DTAC Pty Ltd 2017


DTAC®




PAGE 3 OF 3

DTAC®


EDGING PLEAT INSTALLATION & APPLICATION



SUBSTRATE Vitrified Porcelain / Ceramics / Glass / Metals



SUBSTRATE Carpet / Carpet Tiles



FIXING Screw-fixed or adhesive (screws and plugs supplied)

NOTE DTAC screw-fix mounting methods are available on request

NCC COMPLIANT